

Colour Hardener-Power Floated Datasheet

Sept 2017

Page 1 of 3

A granolithic concrete material that is power floated into fresh topping or concrete which colours, and creates durable and trafficable surfaces for commercial concrete floors. It is a special blend of cement incorporating very hard-wearing aggregates, light fast pigments and certain additives which set rock-hard and which has exceptional abrasion resistance. Some cement floor finishing experience is required for the success of this application.

Purpose

To provide a hard-wearing, attractive colouring system for the surface of concrete, toppings or Cemcrete's SuperScreed, steel floated to a smooth finish.

Technical Data

Type	Cement based surface hardener
Colour	See website www.cemcrete.co.za for colour options
Working time after spreading over surface	Wait for material to wet back before power floating
Initial set	1 Hour
Light floor traffic after application	24 Hours
Compressive strength (28 days)	As per the surface to which it is applied
Application temperature (ambient)	6-25°C
Slab temperature	6-25°C
Min application thickness	2mm
Max application thickness	3mm
Density	2kg/litre
Protection barriers required	Wind and sun barriers (no contact with product)

Advantages

Where pan floated into Cemcrete's SuperScreed it can be used where there are height restrictions between 15mm and 20mm and still achieve good compressive strength and improved abrasive resistance.

Thoroughly colours concrete to a depth of about 2-3mm. No risk of colour being rubbed off or abraded. No need to repaint. Colours are light fast and alkali proof.

Existing Surfaces

All surface beds should have a damp proof membrane.

Where **Colour Hardener** is to be pan floated into SuperScreed that is to be bonded to a concrete slab, these substrates should be integrally sound (no cracking, no crumbling or friability, good compressive strength and good scuff resistance etc.) and of a quality and consistency suitable for application (good mechanical key and level). Cemcrete cannot be held liable should the **Colour Hardener** application be compromised as a result of failure or de-bonding (adhesion failure) occurring between the substrate and newly applied screed due to deficiencies or lack of surface preparation.

Application over moving joints or cracks can result in cracking and delaminating. All construction, cold joints, structural joints and/or structural cracks which may be dynamic before and/or after the **Colour Hardener** application must be extended through to the surface of the **Colour Hardener** application in the form of voided joints. All voided joints including saw cuts should be filled with suitable joint filler.

Cemcrete provides a comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology. Cemcrete believes, to the best of its knowledge, that the information contained herein is true and accurate at the date of issuance and is subject to change without prior notice. For further clarification of these instructions, contact Cemcrete.

Colour Hardener-Power Floated Datasheet

Sept 2017

Page 2 of 3

Where **Colour Hardener** is to be power floated into a concrete or topping base these should be 25MPa minimum where a 13mm or 19mm stone should be used in the mix design. (Stone sizes to be used should be 1/4 to 1/5 the thickness of the slab). Slump to be controlled within a range of 75 to 100mm at point of discharge.

Applications

Recommended for dusting onto wet SuperScreed, concrete or topping when laid prior to pan/power floating.

Site Work

Storage

Unopened bags can be stored on slats in a dry shed for 6 months from date of invoice.

Preparation

Remove all bleed water. Apply **Colour Hardener** to wet concrete/topping or moist SuperScreed before final set has taken place. Please refer to the attached addendum 'A' for the guidelines specific to this type of application.

Weather

Do not apply if rain or temperatures are expected to fall below 6°C within 5 hours of application. Cover during hot, dry weather to avoid premature drying which will halt the hydration process of the cement and reduce the ultimate strength. Do not allow the covers to lie on the surface as this can result in water marks staining the coloured surface.

Mixing

Use in dry powder form for dusting onto concrete, topping or SuperScreed surface before pan/power and steel floating takes place.

Masking

Mask all areas where there is a risk of splashing and staining and where straight edges are required.

Application

A single batch should be used to prevent colour variation.

Concrete base application

As soon as the concrete base has been levelled off and floated, wait for the excess moisture to settle. Remove all bleed water by sponge (DO NOT add additional cement/concrete to absorb this excess water). The surface should be wet, but not glistening with water. See addendum, drying fans may be used.

Spread the **Colour Hardener** powder by dry shake hand method at the rate of about 4kg/m² by dusting directly onto surface and then wait until this has wet back to a damp state. Power float this material to work it into the concrete base as evenly as is possible. For best results apply in two operations; the first with about 4kg/m² (60-70%) of the **Colour Hardener** required and, once power floated, the balance of 2kg/m² (30-40%) to be spread evenly over the surface. Once the water from the surface has wet back into the final layer of Colour Hardener powder added to the surface, finish using a plastic float followed by a hand held steel trowel to a smooth finish.

SuperScreed base application

The SuperScreed should be moist, not wet. **TEST:** Take a fist full of material and close your fist tightly so as to "ball" it in the palm of your hand. When you open your hand the ball should hold its form. Furthermore, a light moisture residue should remain on your hand and should not be glistening wet.

Cemcrete provides a comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology. Cemcrete believes, to the best of its knowledge, that the information contained herein is true and accurate at the date of issuance and is subject to change without prior notice. For further clarification of these instructions, contact Cemcrete.

Colour Hardener-Power Floated Datasheet

Sept 2017

Page 3 of 3

It is imperative that the screed be bonded to the substrate using a single coat of Cemcrete's Concrete Floor Primer applied by sponge and rubbed into the surface and then allowed to dry. The next step is to mix Cemcrete's PrimerCote mixed to a paintable slurry using a mixture consisting of 1 volume FlexBond and two volumes water. Apply the PrimerCote using a block brush and make sure that it is worked into the existing substrate. Whilst this is still wet place the screed material on top of it, then compact and level this material. The PrimerCote must not be allowed to dry before applying the screed material.

Apply the **Colour Hardener** powder by dry shake hand method, or use a plastic container drilled with 3mm holes for even dispersion, at the rate of about 4kg/m² by dusting directly onto surface and pan float to obtain an even colour. For best results apply in two operations; the first with about 4kg/m² (60-70%) of the Colour Hardener required and once pan floated the balance of 2kg/m² (30-40%) to be spread evenly over the surface. Once the water from the surface has wet back into the final layer of **Colour Hardener** powder added to the surface and floated, finish using a hand held steel trowel to a smooth finish.

Curing

Leave to air cure for 1 day after completion. Mist spray with water twice daily for 7 days. This hardening period is to avoid premature drying of the concrete which will reduce the final strength. Allow to cure for a minimum of 14 days before sealing.

Sealing

The moisture in the floor must be less than 5% prior to sealing. Ensure that the surface is free of any form of laitance or dust etcetera before sealing with a suitable sealer fit for purpose in accordance with the manufacturer's instructions. Sealers are best applied to a cool surface in multiple thin coats until an even sheen is achieved. Allow sufficient drying time between coats (product specific in accordance with the manufacturer's instructions). Cemcrete manufacture a wide range of sealers designed for a specific purpose, dry film thickness and durability; (example: for use in wet areas etc.) Various sealers also offer varying final finishes to the surface (e.g.: gloss, matt, colour change, etc.). Please contact your local representative for the best solution to meet your needs.

Coverage

Approximately 3.33m² per 20kg bag.

Floor Maintenance

Maintain **Colour Hardener** floors with Cemcrete's CreteCare Range of floor care products in accordance with the manufacturer's instructions. Sweeping, mopping and vacuuming is a necessity for all floors irrespective of the final finish. Refer to relevant CreteCare data sheets.

Packaging

Colour Hardener supplied in 20kg non-returnable paper bags.

Colours

Please refer to our website: www.cemcrete.co.za for the updated colour choices. It is important to remember that final colours may differ from those depicted on the colour charts as a result of factors such as site conditions and choice of sealer etc. It is important to base your final decision on samples applied by the same contractor and under the same conditions as is governed by the relevant contracting parties. We recommend two samples should be made by the contractor, one for the client and one as a retained sample.

Manufacturer's Warranty

Cemcrete warrants that the products manufactured by it shall be free from material defects and will be consistent with its normal high quality. Should any of the products be proven defective, the liability to Cemcrete shall be limited to replacement of the product ex-factory. Cemcrete makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties expressed or implied. The user shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith.

Cemcrete provides a comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology. Cemcrete believes, to the best of its knowledge, that the information contained herein is true and accurate at the date of issuance and is subject to change without prior notice. For further clarification of these instructions, contact Cemcrete.