

TexCrete Datasheet

June 2012

Page 1 of 2

A thixotropic, quick setting, enhanced fibre-cement blend. Mixed with a solution of FlexBond for the saturation and impregnation of CemForce to form a reinforced product that can be cast into latex or silicone moulds. Produces castings of about 4 to 8 mm in thickness.

Purpose

For the moulding of lightweight small and large intricate castings where fine surface definition is required.

Types

One type only.

Applications

Rock features, pots, ponds, ornaments, small castings, etc. For the manufacture of lightweight pots, door inlays, table tops, ceiling panels, light-fittings, inlays for cupboard doors and furniture, etc. Also for the manufacture of light-weight rock panels that can be pre-made and then fitted on-site to create rock features, ponds, etc.

Colours

Available in light colours like Ivory and Straw. Enhanced using CreteStain once dry. See the CreteStain datasheet for colour range.

Limitations

Will not stick to plastic, rubber or gypsum plaster. The temperature of the FlexBond/water mixing liquid will have an effect on setting time.

Site Work

Storage

Can be stored in a dry shed off the floor on wooden slats for 6 months.

Weather

Do not apply if freezing conditions are expected within 24 hours.

Surface preparation

Mould surfaces should be clean. Depending on the mould material, the surface can, if necessary, be lightly oiled or damped down with clean water.

Mixing

Dilute one volume FlexBond with five volumes clean water and use this solution to mix **TexCrete** to the required consistency.

NOTE: The temperature of the FlexBond/water mixing liquid will have an impact on setting time. If the mixing liquid is too warm, **TexCrete** could flash set. Care should be taken when **TexCrete** is applied by spray or pump.

Application

The bigger the article to be moulded, the more reinforcing required. Although **TexCrete** is heavily fibred, these fibres are not for strength of article but rather to prevent surface cracking or crazing.

Can be applied by brush or low-pressure spray. Apply a thick layer directly onto mould surface. Immediately embed a layer of CemForce or Glass Fibre Mesh into the **TexCrete** layer. Apply further layers within 30 minutes of previous layer. Number of layers of membrane would depend on thickness and strength required.

Cemcrete provides a comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology. Cemcrete believes, to the best of its knowledge, that the information contained herein is true and accurate at the date of issuance and is subject to change without prior notice. For further clarification of these instructions, contact Cemcrete.

TexCrete Datasheet

June 2012

Page 2 of 2

Allow to harden sufficiently before attempting to de-mould. Time depends entirely on mixing and temperature, but would typically be approximately 12 hours. **TexCrete** can also be applied onto a layer of CemForce to create positive work, instead of casting into moulds.

Curing

While **TexCrete** attains very high early set for de-moulding, overall strength is only achieved by curing by wetting with clean water. First allow work to completely dry out before immersing or wetting down with water. The longer this second wetting is carried out, the better the strengths achieved.

Finishing

There are a variety of ways to finish completed castings. Leave as is or stain using Cemcrete's CreteStain. A CreteStain datasheet is available on request.

Sealing

Final surface can be treated by sealing with a dilution of one volume raw linseed oil and two volumes turpentine. When dry, the surface can be polished using a good quality proprietary floor polish. This sealing method is suitable only for articles that will be kept indoors. Surfaces can also be sealed using Cemcrete's Colour Hardener Sealer in accordance with its datasheet. These articles would be suitable for outdoor use.

Coverage

40kg of **TexCrete** will cover approximately 1,5m² when applied 5mm thick.

Packaging

| | |
|------------------|---------------------------------|
| TexCrete | 40kg bags |
| Flexbond | 1, 5 and 20 litre plastic drums |
| CemForce | 1m width with any length |
| Glass Fibre Mesh | 1m widths up to 50m lengths |

Cemcrete provides a comprehensive technical service based on over 3 decades of experience in the field of surface applications and cement technology. Cemcrete believes, to the best of its knowledge, that the information contained herein is true and accurate at the date of issuance and is subject to change without prior notice. For further clarification of these instructions, contact Cemcrete.

Johannesburg Head Office

8 Telford Street
Industria
011 474 2415

Johannesburg Showroom

227 Jan Smuts Avenue
Parktown North
011 447 3149

Centurion Showroom & Warehouse

15 Coachmen's Park
26 Jakaranda Street, Centurion
012 653 6808

Cape Town Showroom & Warehouse

Eagle Park, cnr Bosmansdam &
Omuramba Roads, Montague Gardens
021 555 1034